

<b>Contents</b>	<b>Page</b>
European foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Normative references .....	5
3 Terms and definitions .....	5
4 Principle .....	6
5 Interferences .....	6
5.1 Interference due to carbides.....	6
5.2 Interference due to sulfur and nitrogen compounds.....	7
5.3 Interference due to carbonates.....	7
5.4 Peak does not reach the baseline .....	9
5.5 Difficulties in separating ROC <sub>600</sub> peak and TIC <sub>900A</sub> peak .....	10
5.6 Interferences due to premature releases and deflagrations .....	11
5.7 Interferences due to catalytic active substances in samples.....	11
6 Reagents .....	11
6.1 General.....	11
6.2 Standards for system control.....	12
7 Apparatus.....	13
7.1 Homogenization equipment, e.g. mixer, stirrer, grinders, mills.....	13
7.2 Analytical balance, (precise to at least 0,5 % of the test portion weight). .....	13
7.3 Equipment for determining different carbon types in solids .....	13
8 Procedure.....	13
8.1 General.....	13
8.2 Sample preparation and processing .....	13
8.3 Calibration .....	13
8.4 Measurement (Oxidative method A).....	13
8.5 Measurement (Mixed oxidative/non-oxidative method B) .....	15
9 Evaluation .....	16
9.1 General.....	16
9.2 Control measurements.....	18
10 Expression of results.....	19
11 Test report.....	19
Annex A (informative) Performance characteristics .....	20
Annex B (informative) Cooling procedure for method B .....	30
Bibliography .....	31

## European foreword

This document (EN 17505:2023) has been prepared by Technical Committee CEN/TC 444 “Environmental characterization of solid matrices”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2024, and conflicting national standards shall be withdrawn at the latest by April 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## Introduction

Carbon occurs in soils and materials similar to soil in a variety of compounds and forms. When determining carbon in soils or soil-like materials, an overall determination of the different mass fractions is most feasible. The summarized declaration of carbon is yet done by differentiating organic and inorganic carbon (EN 15936, ISO 10694). In the proportion classified as “organic carbon”, a fraction of very stable highly aromatic and highly condensed carbon compounds can be present, sometimes in significant mass fractions. Since this black (pyrogenic) carbon is only very slowly decomposed and released, its environmental relevance has to be differently evaluated than the proportions of organic carbon which are faster chemical-biologically decomposed. The environmental relevance is estimated if e.g. the suitability of soils and soil-like materials for disposal in landfill is assessed. For a differentiated assessment, a separate declaration of the different mass fractions of organic, black (pyrogenic) and inorganic carbon is necessary. Using the specified temperature-gradient method and utilizing the combustion characteristic(s), the carbon fractions established according to this standard in soil and soil-like materials can be differentiated.

In respect of the hazard potential, the content of solely organically bonded carbon in solids determined with the described method can be important for disposal and/or recycling.

The method has been validated with the materials listed in Table 1, see also Annex A.

**Table 1 — Materials used for validation**

<b>Material type</b>	<b>Materials used for validation</b>
<b>soils from natural material</b>	<b>mineral soils</b> <b>soil with anthropogenic admixtures</b> <b>(urban soils)</b>
<b>tailing material (tailings)</b>	<b>tailing material from coal mining</b>
<b>sediment</b>	<b>sediment</b>
<b>waste</b>	<b>waste incineration ash</b> <b>foundry sand</b> <b>construction waste</b>

## 1 Scope

This document specifies a method for the differentiated determination of the organic carbon content (TOC<sub>400</sub>) which is released at temperatures up to 400 °C, the residual oxidizable carbon (ROC) (including e.g. lignite (brown coal), hard coal, charcoal, black carbon, soot) and the inorganic carbon (TIC<sub>900</sub>) which is released at temperatures up to 900 °C.

The basis is the dry combustion or decomposition of carbon to CO<sub>2</sub> in the presence of oxygen or non-oxygen conditions using temperatures ranging from 150 °C to 900 °C in dry solid samples of sediment, soil, soil with anthropogenic admixtures and solid waste (see Table 1) with carbon contents of more than 1 g per kg (0,1 % C) (per carbon type in the test portion).

NOTE TIC<sub>900</sub> includes the TIC measured after acid addition e.g. by ISO 10694 or EN 15936. TOC<sub>400</sub> is a fraction of TOC measured according to e.g. ISO 10694 or EN 15936.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 16179, *Sludge, treated biowaste and soil - Guidance for sample pretreatment*

EN 15002, *Characterization of waste - Preparation of test portions from the laboratory sample*

ISO 11464, *Soil quality — Pretreatment of samples for physico-chemical analysis*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

### 3.1

#### **total organic carbon which is released up to 400 °C**

##### **TOC<sub>400</sub>**

quantity of carbon which is determined in the range between 150 °C – (400 ± 20) °C to the 1st signal minimum after the minimum holding time at (400 ± 20) °C, in the case of dry combustion in the presence of oxygen

Note 1 to entry: TOC<sub>400</sub> is a fraction of TOC measured e.g. by ISO 10694 or EN 15936.

### 3.2

#### **residual oxidizable carbon measured at 600°C**

##### **ROC<sub>600</sub>**

quantity of carbon which is determined between the signal minima at (400 ± 20) °C and at (600 ± 20) °C after the minimum holding time at (600 ± 20) °C, in the case of dry combustion in the presence of oxygen following method A (procedure see 8.4)

Note 1 to entry: ROC<sub>600</sub> may differ from ROC<sub>900</sub> for some materials